



# SMP 2010

## PREMIUM GRADE TILE ADHESIVE FOR INTERIOR AND EXTERIOR APPLICATION

Classification: C2TE (BS ISO 13007-1:2014)



ECO FRIENDLY



LOW CARBON  
FOOTPRINT



EASE OF USE

### DESCRIPTION

Davco SMP 2010 is a premium grade, polymer modified adhesive that is ideal for interior & exterior applications in residential and commercial work areas. It is specially formulated with low shrinkage and non-horizontal slump properties, making it ideal for installation of high quality tiles on floor and walls.

Davco SMP 2010 has a C2TE classification when tested in accordance to BS ISO 13007-1:2014

### USES

Can be used on both walls and floors, in interior and exterior applications.

Can be used to fix tiles onto concrete, cement renders/screeds, blockwork, rendered brickwork and compatible waterproofing membranes.

Davco SMP 2010 is recommended for the thick and thin bed fixing of all types of ceramic, mosaic, fully vitrified, porcelain, terracotta, slate, quarry, natural stone, granite and marble tiles with the exception of green marble.

When Davco SMP 2010 is modified with Davco Mortaflex ECO (diluted 1:1 with water) it enhances its performance and the system may be used to fix tiles onto facades, screed/render cured for 24 hours and fix tiles in immersed situations (such as swimming pools, spas and similar areas).

### ADVANTAGES

Excellent Open Time

Long repositioning time with extended open time of 30min, which provides greater fixing efficiency over larger areas, therefore increasing productivity.

Excellent Pot Life

The mixed mortar remains useable in a container for up to 3 hours at 20°C, prolonging its usefulness, therefore reducing wastage and saving you money.

### TECHNICAL DATA

Tensile Adhesion Bond Strength 28 days	≥ 1.0 N/mm <sup>2</sup>
Tensile Adhesion Bond Strength After water immersion, 28 days	≥ 1.0 N/mm <sup>2</sup>
Tensile Adhesion Bond Strength After heat ageing, 28 days	≥ 1.0 N/mm <sup>2</sup>
Open Time @ 25 °C	Up to 30 mins
Slip Resistance	≤ 0.5 mm

Specifications are subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

### SURFACE PREPARATION

All surface must be structurally sound, dry, clean and free from movement, oil, grease, wax, curing compounds and other loose or contaminating materials.

Painted surfaces must be scabbled / abraded to expose at least 80% of the original substrate.

Newly rendered / screeded surfaces must be allowed to cure for at least 7 days and have a wood float finish.

Old rendered / screeded surfaces must be thoroughly cleaned prior to tiling and have a wood float finish.

New concrete must be allowed to cure for 6 weeks and should have a wood float finish.

Steel trowel finished concrete must be acid etched or mechanically abraded prior to tiling.

Old concrete surfaces must be thoroughly cleaned prior to tiling. Make sure all release agents are removed from concrete surfaces, especially on tilt-up slabs.

All surfaces, particularly porous surfaces should initially be primed/sealed using Lanko 124 Ultraprime.



**PAREX**  
Building expertise, together





# SMP 2010

## MIXING

Add Davco SMP 2010 to a bucket of clean water mixing constantly until a thick creamy consistency is achieved.

The mixing ratio is 25kg of Davco SMP 2010 to approximately 5.25 - 6.5 litres of water.

Allow the mixture to stand for 5 - 10 minutes, remix, then use the adhesive.

## APPLICATION

Spread the adhesive onto the substrate using either a 6mm x 6mm to 12mm x 12mm notched trowel for wall tiling, or a 12mm x 12mm to 20mm x 20mm notched trowel for floor tiling. The choice of the trowel should be governed by the size of the tiles, depth of knobs, grooves or ridges on the back of the tiles and the evenness of the substrate.

Spread approximately 1.2 - 1.5m<sup>2</sup> at one time. Ensure that the adhesive is wet when the tiles are laid and tapped into position to ensure positive contact with the adhesive.

For dual bonding, follow the above-mentioned instructions, after buttering the underside of the tile.

Ensure there are no voids under the tiles.

Do not allow the adhesive to skin over prior to tiling.

## Grouting after tile installation

Grouting should preferably be carried out at least 24 hours after the completion of tiling.

Pour clean water, or if any movement is anticipated, Davco Mortaflex ECO in a clean mixing bucket.

Slowly add the grout powder, stirring continuously until a lump-free, toothpaste consistency is achieved.

Using a rubber float or squeegee, work the grout paste deep into the joints, making sure the grout is not just sitting on top.

Remove excess grout from the surface of the tiles with the float or squeegee using a diagonal motion to avoid dislodging the embedded grout.

A primary clean up should be done by wiping with a damp cloth or sponge.

For enhanced colour and increased grout's flexibility and water resistance, use Davco Sanitized® Coloured Grout ECO (CFG).

## PACKAGING

Davco SMP 2010 is available in 25kg bags.

## COVERAGE

Using a 6mm X 6mm notched trowel, approx. 3.5 kg/m<sup>2</sup>

Using a 12mm X 12mm notched trowel, approx. 7.0 kg/m<sup>2</sup>

Using a 20mm X 20mm notched trowel, approx. 11.9 kg/m<sup>2</sup>

## SHELF LIFE

The shelf life is up to 12 months when stored unopened in elevated, cool and dry conditions.

## PRECAUTIONS

Not suitable for moisture sensitive stone, please use Davco 2-Part Rapid instead.

Do not allow the adhesive to skin prior to laying the tiles. If the adhesive skins remove and dispose of it, then re-apply fresh adhesive.

Do not apply in temperatures above 35°C or below 10°C. In cool and / or humid conditions, allow longer setting times.

For winter application consult with manufacturer on suitability.

## CLEANING

Avoid excessive adhesive drying out as it is easier to remove when it is still fresh.

Remove wet product with a damp cloth.

Clean tools and equipment with water.

If allowed to dry it will need to be removed mechanically or using a suitable acid based product. In some cases these methods can affect the tile and should be avoided whenever possible.

## HEALTH & SAFETY

This product contains cement which is alkaline and can cause dermatitis. It is recommended that applicators wear PVC or similar gloves and safety goggles. If skin irritation occurs, seek medical attention promptly. Refer to safety data sheet.

## Disclaimer

The use of this product is beyond the manufacturer's control and liability is restricted to the replacement of material proven faulty. The manufacturer is not responsible for any loss or damage arising from incorrect usage. Specifications are subjected to changes without prior notice. Before application, customers and users are requested to check that they have the latest version of this document from our website [www.parexgroup.com.sg](http://www.parexgroup.com.sg)

## PAREXGROUP PTE LTD

28 TUAS SOUTH AVENUE 8, SINGAPORE 637648

TEL: (65) 6861 0632 FAX: (65) 6862 3915

EMAIL: SALES@PAREXGROUP.COM.SG

WEBSITE: WWW.PAREXGROUP.COM.SG

ONLINE STORE: DAVCO-ONLINE.COM.SG

ParexGroup, a French multi-national company with headquarters in Paris, is a leading manufacturer of speciality products for the construction industry with operations in more than 20 countries, and our 2700 people around the world are the cornerstone of our growing organization.

Updated TA61 Jul 2018



Certificate SG09/02195



Certificate SG95/06111



Certificate SG09/50075



Certificate GMS-C / GHG / 0002

